

HYTAC[®] - B1X

**Tough Easily Machined
Syntactic Tooling**

Technical Bulletin



CMT MATERIALS, Inc.
107 Frank Mossberg Drive
Attleboro, MA 02703
TEL (508) 226-3901 FAX - 3902
email: info@cmtmaterials.com
www.cmtmaterials.com

Innovative Tooling Materials for Thermoforming

Overview

HYTAC-B1X is the first plug assist material to combine the toughness of engineering thermoplastics with the low thermal conductivity of a syntactic foam. Plug assists made from *HYTAC-B1X* will resist the chips and dings associated with production abuse while reducing mark-off and sticking of difficult to process polymers. *HYTAC-B1X* maintains the high thermal stability required to process today's thermoformed polymers. In addition, *HYTAC-B1X* eliminates the machining difficulties of conventional syntactic foams. ***This product does not produce dust during machining and finishing of plugs.***

- **High Toughness and Durability**

With high toughness, machine downtime due to damaged plugs is reduced. Less downtime = lower costs = more consistent quality.

- **Superb Machinability**

No dust collection equipment or respirators are required due to the large, non-abrasive chips. Plugs can be machined over three times faster than syntactic foam due to the easy chip formation. ***No more complaints from your machinists.***

- **Excellent Temperature Resistance**

HYTAC-B1X is specially formulated for service up to 350°F with minimal loss in mechanical properties.

- **Variety of Shapes and Sizes**

The material is provided in standard sized rods or sheets, but may be custom molded to meet your specific needs.

Applications

HYTAC-B1X may be used in a wide variety of applications on sheet-fed, rotary, or in-line machines. It may also be used with most commonly thermoformed materials, and has proven quite effective with polypropylene and other polyolefins.



Typical Properties

Property	<i>HYTAC-B1X</i>
Color	Light Blue
Density (ρ)	40-45 lb/ft ³ [640- 721 kg/m ³]
Thermal Conductivity (k)	0.11 BTU /hr-ft-°F [0.18 W/m°K]
Specific Heat (C_p) per mass	0.43 BTU/(lb•°F) [1.80 kJ/(kg•°C)]
Coefficient of Thermal Expansion (CTE)	34.3 x 10 ⁻⁶ in/in/°F [61 x 10 ⁻⁶ m/m/°C]
Compressive Strength	7,100 psi [49.2 Mpa]
Compressive Modulus	298 Ksi [2.05 Gpa]
Service Temperature	350 °F [180 °C]